



solutii profesionale pentru etansare

Temafast Economy

INFORMATII				
Presiunea maxima de lucru	MPa	4		
Temperatura maxima de lucru	°C	Continuu	140	Abur 120
		Maxim	210	
Utilizare: apa, abur, gaz, ulei, alcool, combustibil, produse chimice de baza				
PARAMETRII TEHNICI			Standard corespunzator	
DENSITATE	g.cm-3	1,6-1,9	DIN 28 090 - 2	
REZISENTA REZIDUALA* 16H/175°C	MPa	20	DIN 52 913	
COMPRESIE	%	5-15	ASTM F 36 J	
RECUPERARE min.	%	50	ASTM F 36 J	
RATA DE DISPERSIE max.	mg/(s.m)	0,1	DIN 3535 – 6	
REZISTENTA LA FLUIDE - IN FUNCTIE DE GROSIME				
ASTM ULEI - IRM 903, ČSN ISO 1817 5 h/150 °C max.	%	10	ASTM F 146	
ASTM COMBUSTIBIL B - ČSN ISO 1817 5 h/23 °C max.	%	15	ASTM F 146	
FLEXIBILITATE	Fara rupturi sau spatii		ASTM F 147	
CULOARE, TIPARIRE	Galben, marcat pe o singura parte TEMAFAST ECONOMY DIN 28 091 – 2 FA-Z-12-0 ASTM F 104 F 712 120 M4			
NOTA: a) Parametrii sunt valizi pentru grosimi ale placilor de la 2mm b) *Valoare valabila de la grosime de 1,5mm				
CERTIFICARI: DNV-GL, WRAS,TZW,PZH,GOST, UA - Tesko				
Dimensiuni standard: 1500x1500mm; 1500x1000mm; 1500x3000mm				
Gosimi standard: 2mm, 3mm, 4mm, 5mm				
Cod Produs wdb20 www.etans.ro	Pag1	Aprobat: 27.4.2015	Valabil din: 28.4.2015	

Testat in conformitate cu:TP-62-085-15